

# PLASTIC SUPER

## Product description

PLASTIC SUPER is a fully matt high quality emulsion paint for interior use. It shows excellent opacity and surface coverage with great workability while applying easily and flowing perfectly. It offers very good adherence to older and new surfaces giving outstanding opacity and very good resistance in washability and shelf-life time. It is almost odourless. The finished surface is a homogenic fully mat result.

## Technical properties

*Color: White, 8 basic shades and unlimited number of shades through the THE XRO.MA COLOR SYSTEM.*

*Density:* 1.46 ± 0.05 g/ml  
(EN ISO 2811-1)

*Viscosity:* 115 ± 5 KU  
(ASTM D 562)

*pH:* 8-9.5  
(EN ISO 19396-1)

*Water Vapor Permeability:* Sd=0.24±0.02 m  
(EN ISO 7783, 0.14 <Sd<1.4, medium class II)

*Water Permeability:* w=0.07 ± 0.02 kg. / m<sup>2</sup>h<sup>0.5</sup>  
(EN ISO 1062-3, W3 low, w< 0,10 kg/m<sup>2</sup>h<sup>0.5</sup>)

*Adhesion:* ≥1.70 MPa  
(EN ISO 4624)

*Gloss value:* < 5, Dead Matt  
(EN ISO 2813: <5, at 85°)

*Opacity:* ≥ 98.5%  
(EN ISO 6504-3) (consumption ≥11 m<sup>2</sup>/l)

*Whiteness:* ≥ 89  
(EN ISO 6504-3)

*Wet-scrub resistance:* CLASS 1  
(EN ISO 11998: <5 µm in 200 wash cycles)

*Touch dry:* ½ -1 hour (+23°C)

*Time to repaint:* 3-4 hours (+23°C)

## Substrate Preparation

PLASTIC SUPER is applied in interior substrates like gypsum boards, plasters, concrete to older

and new surfaces after their priming with adequate primer. Substrate should be clean and free of loose materials or dust and grease or oily materials etc. that can create lower adherence. Any other cracks or voids on the substrate should be filled with acrylic sealant or adequate products. Application of Acrylic Primer diluted with water to 1:3 till 1:4 follows as primer. In case of Gypsum Board the use of Acrylic Gypsum Board Primer is suggested with a 10% dilution with water. Otherwise in case of a Water paint or very loose material or high dust substrate a Micronized Acrylic Primer is suggested for use after a 50 % dilution with water. Depending on the absorption of substrate a 100-200 g/m<sup>2</sup> of diluted primer is recommended. In case the surface is in good condition from older application with same type/ quality of paint the priming stage could be avoided.

## Products Application

PLASTIC SUPER is diluted with potable water 5-10% and stirred smoothly. It is applied in 2 layers and the best result is managed with a consumption of 12 m<sup>2</sup>/lt per layer.

Rolls brushes and airless guns might be used for product applications and should be cleaned with water and detergents immediately after application.

Application of the product should be avoided if temperature is above or lower than 7-35 °C and humidity exceeds 80% due to probable effect on product properties.

## Packaging

PLASTIC SUPER is supplied in containers of 0.75lt, 3 lt, 10 lt.

## Shelf Life -Storage Conditions

The product has a shelf life of 24 months in tight closed canisters and should be stored between 5-35°C, also avoid exposure of packaging to direct sunlight and frost.

# PLASTIC SUPER

## Volatile Organic Compounds

According to Directive 2004/42/  
(Annex II, table A),  
the maximum allowed VOC content  
for the product subcategory a,  
type WB is 30 g/lit (2010) for the ready-to-use product.  
The ready-to-use product PLASTIC SUPER contains VOC  $\leq 2$  g/lit.

## **TO XROMA**

21st KM O.N.R.Thessaloniki - Kavala -P.C. 57200/Tel. 2394052451/Info: [www.toxroma.gr](http://www.toxroma.gr)



The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore, the user is responsible for confirming that the chosen product is suitable for the application. Number /date of issue 01/ 06-03-2023.